

Grades:	<u>Carbonless Copy Paper, Blue Images</u>
Regular basis weights (gsm):	45, 50, 55, 80 CB white or tinted; 47, 50, 55, 80 CF white or tinted; 50, 52 CFB white or tinted;
Basis Weight variation:	±5%;
Caliper Variation (CD):	=5µm for basis weights 50g/m ² or less; =7µm for basis weight greater than 50g/m ²
Paper Density:	0.70-0.85 g/cm ³ ;
Opacity:	=65%;
Smoothness (CF both sides):	=80 s;
Whiteness:	=87% with OBA; ≥78% without OBA;
Chromatic deviation:	≤2.0% (coated side for tinted grades);
Curls:	≤12 mm
Optical density _D (5min):	≥0.60 CB rolls and sheets, 3 ply prints; ≥0.70 CFB rolls, 5 ply prints; ≥0.65 CFB sheets, 5 ply prints; ≥0.75 CF, 5 ply prints;
Imaging Sensitivity (3 ply prints):	ΔE≥88%; ΔD≥88%;
Surface strength (medium viscosity printing ink):	≥0.5 m/s (printing side);
Light resistance (residual I_{E} after 144 hrs):	≥50%;
Friction resistance (I_{E}):	≤5%;
TSI (MD):	≥60 N.m/g;
Surface PH:	6.0-9.0
Moisture on delivery:	≤8.0% CB and CFB sheets; 6.0%-7.5 % CB and CFB rolls; 6.5%-7.5% CF;
Regular roll sizes:	120-600mm, paper length = 6,000 m;
Regular sheet sizes:	787*1092, 889*1194, 890*600, 880*615, 700*1000;
Export Packing:	Wrapped inside with thin plastic film against moisture, and outside with heavy craft paper for sheets, corrugated paperboard for rolls.

Grades:	<i>Carbonless Copy Paper, Black Images</i>
Regular basis weights (gsm):	45, 50, 55, 80 CB white or tinted; 47, 50, 55, 80 CF white or tinted; 50, 52 CFB white or tinted;
Basis Weight variation:	±5%;
Caliper Variation (CD):	≤5µm for basis weights 50g/m ² or less; ≤7µm for basis weights greater than 50g/m ²
Paper Density:	0.70-0.85 g/cm ³ ;
Opacity	≥65%;
Smoothness (CF both	≥80 s;
Whiteness:	≥87% with OBA;
Chromatic deviation:	≤2.0% (coated side for tinted grades);
Curls:	≤12 mm
Optical density (D (5min):	≥0.30 (3 ply prints)
Imaging Sensitivity:	ΔE≥88%; ΔD≥88% (3 ply prints);
Surface strength (medium	≥0.5 m/s (printing side);
Light resistance (residual %	≥50%;
Friction resistance (%E):	≤5%;
TSI (MD):	≥60 N.m/g;
Surface PH:	6.0-9.0
Moisture on delivery:	≤8.0% CB and CFB sheets; 6.0%-7.5 % CB and CFB rolls; 5.0%-7.5% CF;
Regular roll sizes:	120-600mm, paper length = 6,000 m;
Regular sheet sizes:	787*1092, 889*1194, 890*600, 880*615, 700*1000;
Export Packing:	Wrapped inside with thin plastic film against moisture, and outside with heavy craft paper for sheets, corrugated paperboard for rolls.